



US006306966B1

(12) **United States Patent**  
**Horie et al.**

(10) Patent No.: **US 6,306,966 B1**  
(45) Date of Patent: **Oct. 23, 2001**

(54) **MOISTURE CURABLE COMPOSITION**

(75) Inventors: **Yasunobu Horie; Yoshinobu Egawa;**  
**Yuichi Oshima; Hideharu**  
**Hashimukai; Tomokazu Wakaume;**  
**Hiroshi Aoki**, all of Tokyo (JP)

(73) Assignee: **Cemedine Co., Ltd.**, Tokyo (JP)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **09/422,084**

(22) Filed: **Oct. 21, 1999**

(51) Int. Cl.<sup>7</sup> ..... **C08L 71/02**

(52) U.S. Cl. .... **525/106; 525/404; 528/901;**  
**524/493**

(58) Field of Search ..... **525/106, 404;**  
**528/901; 524/493**

(56) **References Cited**

**U.S. PATENT DOCUMENTS**

5,109,064 \* 4/1992 Wakabayashi et al. .

**FOREIGN PATENT DOCUMENTS**

0 339 666 A2 11/1989 (EP) .  
0 525 769 A1 2/1993 (EP) .  
0 541 074 A2 5/1993 (EP) .

**OTHER PUBLICATIONS**

Kroshwitz, Encyclopedia of Chemical Technology, 4th Ed., vol. 21, Wiley-Interscience, p. 1023.\*

\* cited by examiner

*Primary Examiner*—Robert Dawson

*Assistant Examiner*—Kuo-Liang Peng

(74) *Attorney, Agent, or Firm*—Arent Fox Kintner Plotkin & Kahn, PLLC

(57) **ABSTRACT**

A moisture curable composition excellent in transparency, operating efficiency and storage stability, and is suitable for use as an adhesive and a sealing material is provided. The moisture curable composition produced by blending 100 parts by weight of a mixture (A) and 2 parts by weight to 300 parts by weight of amorphous powder (B). The mixture (A) comprises (1) a copolymer having reactive silicon groups which can be cross-linked by hydrolysis, whose molecular chain substantially consists of (i) alkylacrylate and/or alkylmethacrylate monomeric units having an alkyl group with 1 to 8 carbon atoms, and (ii) alkylacrylate and/or alkylmethacrylate monomeric units having an alkyl group with 10 or more carbon atoms, and (2) a polymer substantially consisting of oxyalkylene including reactive silicon groups which can be cross-linked by hydrolysis. The amorphous powder (B) has a grain diameter ranging from 0.01  $\mu\text{m}$  to 300  $\mu\text{m}$ .

**4 Claims, No Drawings**